

Legend®

▶ POLERA COOLDRY LEGEND

• CARACTERÍSTICAS •

- ⊕ Polera Técnica de tejido Cooldry.
- ⊕ Tecnología cooldry de secado rápido, simula la porosidad de la piel.
- ⊕ Posee nivel de protección solar.
- ⊕ Medio cierre para regular temperatura corporal.
- ⊕ Sesgo reflectivo en cierre.
- ⊕ Disponible en azul marino.
- ⊕ Gramaje: 140 grs.
- ⊕ Modelo Unisex. Curva de XS a XXL.

XS	• Cód: 1119413915
S	• Cód: 1119414015
M	• Cód: 1119414215
L	• Cód: 1119414315
XL	• Cód: 1119414415
XXL	• Cód: 1119414515



**SESGO REFLECTIVO
EN CIERRE**



**SECADO
RÁPIDO**



RESPIRABLE



LIVIANO



COMFORTABLE



FILTRO UV



**EVACUACIÓN
DE HUMEDAD**

IMPORTADO POR

TEST REPORT

Number: GZHT02214851

Sample Description As Declared :

No. Of Sample : Two
Fibre Content : 100%Polyester
Material : Knitted Fabric, marked as (A-B)
Finishing : -
End Uses : Adult's Garment
Season : -
Colour : A: BLACK
 B: YELLOW
Style No. : -
Order No./PO No. : -
Buyer's Name : ACETOGEN GAS CHILE S.A.
Manufacturer's Name : -
Ref. : -

Prepared And Checked By:
For Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch



Lin Lin
General Manager

Sherry / mikechan



Page 1 Of 4

Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch

3/F, Hengyun Building, 235 Kaifa Ave., Guangzhou
Economic & Technological Development District, Guangzhou, China
深圳天祥质量技术服务有限公司广州开发区分公司
中国广州经济技术开发区开发大道 235 号恒运大厦 3 楼
Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode:510730
www.intertek.com

Applicant's Provided Care Instruction/Label :

-

Date Received/Date Test Started : Oct 23, 2019

Date Final Information Confirmed: -

Prepared And Checked By:
For Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch



Lin Lin
General Manager

Sherry / mikechan



TEST REPORT

Number: GZHT02214851

Tests Conducted (As Requested By The Applicant)

1 Determination Of The UVR Transmission Of Dry Textile As Received (BS EN 13758-1:2002+A1:2006):

Solar Spectrum Irradiance Used : Noonday, July 3, Sunlight, Albuquerque, nm.

No. Of Scans : 8

The Samples Are Tested In Dry And Relaxation State.

Temperature : 20±2°C

Relative Humidity : 65±2%

The Ultraviolet Protection Factor, UPF:	(A)
	> 50
% Of Mean UVA Transmittance, UVA Average:	2.27%
% Of Mean UVB Transmittance, UVB Average:	1.49%
Standard Deviation Of UPF:3.74	3.74
Standard Deviation Of UVA:	0.11%
Standard Deviation Of UVB:	0.09%
UPF Of Each Specimen:	
1.	57.63
2.	62.42
3.	61.61
4.	58.60
5.	63.03
6.	62.33
7.	69.91
8.	60.21

Sherry / mikechan

Page 3 Of 4

Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch

3/F, Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

深圳天祥质量技术服务有限公司广州开发区分公司

中国广州经济技术开发区开发大道 235 号恒运大厦 3 楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode:510730

www.intertek.com

TEST REPORT

Number: GZHT02214851

Tests Conducted (As Requested By The Applicant)

The Ultraviolet Protection Factor, UPF:	(B)
	47
% Of Mean UVA Transmittance, UVA Average:	3.36%
% Of Mean UVB Transmittance, UVB Average:	1.82%
Standard Deviation Of UPF:	0.60
Standard Deviation Of UVA:	0.04%
Standard Deviation Of UVB:	0.02%
UPF Of Each Specimen:	
1.	48.76
2.	47.78
3.	47.87
4.	49.10
5.	49.03
6.	48.53
7.	48.73
8.	49.54

Remark : Rated UPF requirement is 40+, as stated in BS EN 13758 Part 2 (2003+A1:2006).

End of Report

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct. No copy of the test report(except for full text copy) shall be made without the written approval by Intertek.

Sherry / mikechan

Page 4 Of 4

Intertek Testing Services Shenzhen Ltd. Guangzhou GDD Branch

3/F, Hengyun Building, 235 Kaifa Ave., Guangzhou

Economic & Technological Development District, Guangzhou, China

深圳天祥质量技术服务有限公司广州开发区分公司

中国广州经济技术开发区开发大道 235 号恒运大厦 3 楼

Tel: +86 20 8396 6868 Fax: +86 20 8222 8169 Postcode:510730

www.intertek.com